

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 447 094 A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **91301797.6**

(51) Int. Cl.⁵: **C01F 11/18, D21H 17/67**

(22) Date of filing: **05.03.91**

(30) Priority: **13.03.90 US 493075**

(43) Date of publication of application:
18.09.91 Bulletin 91/38

(84) Designated Contracting States:
BE CH DE ES FR GB IT LI NL SE

(71) Applicant: **PFIZER INC.**
235 East 42nd Street
New York, N.Y. 10017(US)

(72) Inventor: **Kunesh, Charles J.**
3305 Altonah Road
Bethlehem, Pennsylvania 18017(US)
Inventor: **Passaretti, June D.**
480 Lyons Road
Liberty Corner, New Jersey 07938(US)

(74) Representative: **Bradbrook, Geoffrey William**
et al
PFIZER LIMITED Ramsgate Road
Sandwich Kent, CT13 9NJ(GB)

(54) **Rhombohedral calcium carbonate and accelerated heat-aging process for the production thereof.**

(57) A form of calcium carbonate having a blocky-six-sided rhombohedral final crystal morphology, with a surface area of from about 3 to about 15 m²/g, an average discrete particle size of from about 0.2 to about 0.9 microns, wherein the discrete particles have an aspect ratio less than 2, and a particle size distribution such that at least about 60 weight percent of the particle lies within 50 percent of the equivalent discrete particle spherical diameter, suitable for use as a filler material in papermaking to improve the optical properties of the resulting paper, is disclosed. An accelerated heat-aging process, including embodiment thereof which utilize hydrothermal techniques, for rapidly producing this form of calcium carbonate and a related form of calcium carbonate having a prismatic final crystal morphology in large quantities to meet the demand of the papermaking industry, as well as a method for using these materials in papermaking are also disclosed.

EP 0 447 094 A1

This invention relates to calcium carbonate having a specified crystal morphology, average particle size, particle size distribution and surface area, a process for producing this form of calcium carbonate product, and a method of use of the product as a filler material, for example, in papermaking, to improve the optical properties of the resulting paper.

5 The present trend in papermaking is toward the manufacture of sheets with higher brightness and opacity. This type of paper is now made mostly through the use of extenders such as calcined clay and titanium dioxide. These materials present a number of disadvantages, however, in that they are rather expensive and unavailable in sufficient supply to satisfy the needs of large scale paper manufacturers. The competition for the limited quantities available further causes the price of these materials to remain high or
10 to further increase. Consequently, their use is effectively limited to high grade, expensive papers which are usually produced in more limited quantities.

The papermaking industry has been clamoring for the development of a filler-extender material which is inexpensive, available in large quantities and which provides the desired properties in the final paper.

Precipitated calcium carbonate has been used as a filler material in paper for many years. Precipitated
15 calcium carbonate has the advantage of being able to be produced in large quantity at relatively low cost. Therefore, it was decided to develop a form of precipitated calcium carbonate having a morphology which when used as a filler or extender in paper, affords the high level of brightness and opacity in the final paper product comparable to that achieved with the more expensive calcined clay and titanium dioxide filled papers.

20 One method of altering the morphology of a crystalline substance, such as precipitated calcium carbonate, in order to change its properties, is by Ostwald ripening or heat-aging.

Conventional heat-aging, also known as Ostwald ripening, is a process whereby crystals, such as of calcium carbonate, initially at a higher internal energy state, and having a relatively small average particle size and relatively high phase solubilities, undergo a phase transformation by dissolving and redepositing
25 on crystals at a lower internal energy state. The process results in a final crystal product characterized by greater perfection of its crystal lattice structure, a narrower particle size distribution, greater degree of particle discreteness and lower surface energy.

The procedure for conventional heat-aging of precipitated calcium carbonate produced by the reaction of calcium hydroxide and carbon dioxide is to endpoint the precipitated calcium carbonate synthesis at pH
30 8.0, screen the material to remove the impurities, and heat a 10% by weight solids slurry to the aging temperature (usually 80° C). The pH of the system rises to approximately 10.5 due to the unreacted Ca-(OH)₂ in the slurry. The aging reaction can be monitored by measuring the surface area of the calcium carbonate at hourly intervals.

Unfortunately, conventional heat-aging is a slow, time consuming and highly capital intensive process.
35 Heat-aging of calcium carbonate with an initial morphology having a higher surface area and smaller average particle size to a final morphology having a surface area of from about 3 to about 15 m²/g and an average discrete particle size of from about 0.2 to about 0.9 microns typically takes extended periods of time ranging up to several hundred hours, depending in part on the degree of purity of the starting material and the aging temperature. The time required for heat-aging is inversely dependent on the purity of the
40 starting material, the purer the material, the shorter the aging time required. Calcium carbonates containing impurities such as magnesium carbonate, at levels as low as several weight percent, require considerably longer heat-aging time to rearrange their morphologies. The time required for heat-aging is also inversely dependent on the aging temperature; a longer time is required at lower temperatures, and a shorter time is required at higher temperatures. In order to produce commercial scale quantities of product obtained by the
45 conventional heat-aging process, large equipment volumes are needed, thus making this process uneconomical.

The primary objective of the present invention is a high opacifying, high brightness material that is applicable at a paper machine's wet end, size press, or coating stage and is competitive with current expensive fillers such as calcined clay and titanium dioxide, and a process for the rapid, cost effective
50 production of such material in large quantity.

Heat-aged calcium carbonate of rhombohedral morphology, having a surface area of from about 3 to about 15 m²/g, an average discrete particle size of from about 0.2 to about 0.9 microns, wherein the discrete particles have an aspect ratio less than 2, and a particle size distribution such that at least about 60 weight percent of the particles lie within 50 percent of the equivalent discrete particle average spherical
55 diameter, when utilized as a filler in the manufacture of paper, results in a paper product that demonstrates a significant improvement in performance with respect to the optical properties of the paper over any previously made paper utilizing other forms of calcium carbonate as the filler material.

In order to meet the demand for large quantities of heat-aged calcium carbonate having these

properties, it was desired to determine a way to significantly shorten the amount of time required for heat-aging. Accordingly, this invention teaches an accelerated process for heat-aging which is particularly adapted to producing large amounts of heat-aged calcium carbonate having properties which make it an unexpectedly superior filler material in papermaking. The product produced by the accelerated heat-aging process of the present invention is also useful as a filler for rubber, plastics, paint, food products, synthetic resins and the like.

The accelerated heat-aging process of the present invention involves the adjustment of the pH of the calcium carbonate at the aging temperature to about 6.5, followed by the addition of an alkali metal hydroxide, preferably sodium hydroxide, to the calcium carbonate, to raise the pH to from about 9.5 to about 12.0.

Fig. 1 shows the specific surface area over time of samples of ultrafine precipitated calcium carbonate prepared according to both the accelerated heat-aging process and the conventional heat-aging process.

Fig. 2 is a particle size distribution curve of rhombohedral calcium carbonate showing the narrow size distribution.

Fig. 3 is a photomicrograph of the crystal morphology of particles of precipitated calcium carbonate heat-aged by the accelerated heat-aging process.

Fig. 4 is a photomicrograph of the industry standard non-heat-aged precipitated calcium carbonate having a scalenohedral rosette structure.

Fig. 5 is a comparison of pigment scattering coefficient in handsheets versus the percent filler content for various forms of heat-aged ultrafine precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 6 is a comparison of brightness in handsheets versus the percent filler content for various forms of heat-aged ultrafine precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 7 is a comparison of handsheet opacity versus the percent filler content for various forms of heat-aged ultrafine precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 8 shows handsheet opacity versus specific surface area for various heat-aged ultrafine precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 9 shows pigment scattering coefficient versus specific surface area for various heat-aged ultrafine precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 10 is a transmission electron micrograph of non-heat-aged ultrafine precipitated calcium carbonate showing initial crystal morphology before heat-aging.

Fig. 11 is a transmission electron micrograph of heat-aged ultrafine precipitated calcium carbonate showing the rhombohedral morphology.

Fig. 12 is a transmission electron micrograph of non-heat-aged scalenohedral precipitated calcium carbonate.

Fig. 13 is a transmission electron micrograph of heat-aged scalenohedral precipitated calcium carbonate showing the prismatic morphology.

Fig. 14 shows pigment scattering coefficient versus percent filler content in handsheets for various forms of heat-aged precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 15 shows opacity versus percent filler content in handsheets for various forms of heat-aged precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 16 shows brightness versus percent filler content in handsheets for various forms of heat-aged precipitated calcium carbonate and non-heat-aged precipitated calcium carbonate fillers.

Fig. 17 shows specific surface area versus time for various heat-aged ultrafines, heat-aged at various temperatures.

Fig. 18 shows a comparison of the aging rates between 80°C and 200°C for the accelerated heat-aging process using hydrothermally aged and non-hydrothermally aged starting materials.

Fig. 19 is a photomicrograph of hydrothermally heat-aged ultrafine precipitated calcium carbonate showing the rhombohedral morphology.

While not wishing to be limited to a particular theory to explain the basis for the significant improvement in the time required for heat-aging according to the present process, we believe that the reduction in heat-aging time is attributable to the presence of a high concentration of hydroxide ions produced by the dissociation of the alkali metal hydroxide added to raise the pH. The hydroxide ions supplied by the dissociated alkali metal hydroxide act to suppress the phenomenon, known to those skilled in the art as "flashback". Flashback is the dissociation of calcium hydroxide, which is entrained in all forms of calcium carbonate at some level of concentration, even in high purity calcium carbonate. Calcium ions produced by the dissociation of calcium hydroxide are responsible for interfering with and inhibiting the rate of the conventional calcium carbonate heat-aging recrystallization process, thereby causing the lengthy time

required for conventional heat-aging. The calcium ions prevent the dissociation of calcium carbonate which in turn hinders the recrystallization phase of the heat-aging process. In the accelerated heat-aging process of the present invention, the presence of the high concentration of hydroxide ions supplied by the dissociating alkali metal hydroxide added to the calcium carbonate causes an equilibrium shift in the reverse direction to suppress dissociation of the entrained calcium hydroxide in the calcium carbonate, resulting in a more equal concentration of calcium and carbonate ions in the recrystallization mixture, which greatly speeds up the heat-aging recrystallization process.

According to the accelerated heat-aging process of the present invention, the crystal morphology of calcium carbonate is rearranged from an initial morphology having a surface area of greater than about 15 m²/g and an average discrete particle size of from about 0.01 to about 0.8 microns, to a final morphology having a surface area of from about 3 to about 15 m²/g, and an average discrete particle size of from about 0.2 to about 0.9 microns.

As defined herein, average discrete particle size refers to the equivalent spherical diameter of an individual particle which can exist as an individual particle or as part of a cluster or agglomerate, as opposed to the equivalent spherical diameter of the cluster or agglomerate itself.

The process comprises the steps of initiating heat-aging of the calcium carbonate by heating it to an aging temperature of from about 40 to about 100 °C; adjusting the pH of the calcium carbonate at the aging temperature to about 6.5, such as by addition of carbon dioxide; adding an alkali metal hydroxide to the calcium carbonate at the aging temperature to raise the pH to from about 9.5 to about 12.0; maintaining the calcium carbonate at the aging temperature for a sufficient time to cause the morphology of the calcium carbonate to rearrange to the final form; and terminating heat-aging to fix the morphology of the calcium carbonate in the final form.

The process of the present invention can be applied to calcium carbonate either as precipitated calcium carbonate or as fine ground natural limestone.

The calcium carbonate can be in a form either as a dry powder, which is subsequently slurried, or as an aqueous slurry. When the calcium carbonate is used in the form of an aqueous slurry, it has been found that a slurry having about a 10 weight percent calcium carbonate solids content is preferred.

The alkali metal hydroxide can be a hydroxide of any metal from group IA of the periodic table. Sodium hydroxide is preferred. It has been found that calcium hydroxide is not effective for use in adjusting the pH of the calcium carbonate at the aging temperature. This is believed to be due to the presence of the calcium ions formed on dissociation of the calcium hydroxide inhibiting the dissolution of calcium carbonate, thus slowing the aging process.

The amount of alkali metal hydroxide added to the calcium carbonate is in an amount of from about 0.1 to about 15 weight percent, based on the dry weight of calcium carbonate. The alkali metal hydroxide added to adjust the pH can be pure or an aqueous alkali metal hydroxide solution. Sodium hydroxide is the preferred alkali metal hydroxide.

The length of time the calcium carbonate must be maintained at the aging temperature in order to recrystallize to the new morphology is determined by both the initial morphology of the calcium carbonate and the nature and extent of any impurities present in the calcium carbonate.

Where the calcium carbonate starting material has an initial average particle size of from about 0.01 to about 0.5 microns and has a high purity, the aging time is as short as about 60 minutes. For calcium carbonate starting material having a larger initial agglomerated particle size of from about 0.5 to about 2 microns, and/or containing impurities, particularly such as magnesium carbonate, of up to about 5 weight percent, the heat-aging time can be as long as 24 hours.

When the calcium carbonate has been heat-aged sufficiently long so that transformation of the calcium carbonate crystal morphology is complete, the heat-aging process must be terminated to fix the morphology in the desired state, and prevent further recrystallization.

Heat-aging can be terminated by either reducing the temperature to below about 40 °C; by reduction of the pH; or by a combination of temperature and pH reduction.

It has been found that heat-aging does not occur or proceeds at such a slow rate as to be insignificant when the temperature is reduced to about 40 °C or below. The heat-aging process is also very pH sensitive and a reduction of the pH to below about 8.5 effectively halts heat-aging and further recrystallization of the calcium carbonate.

Termination of heat-aging by temperature reduction can be effected rapidly by quenching the calcium carbonate, such as by immersion in an ice bath.

Termination of heat-aging by pH reduction is effected by addition of CO₂ or of a polybasic acid to the calcium carbonate. The polybasic acid is preferably phosphoric acid.

Calcium carbonate can also be heat-aged according to further embodiments of the process of the

present invention which utilize hydrothermal techniques.

It has been found that heat-aging in a hydrothermal bomb under hydrothermal conditions of high temperature, up to about 300° C and under elevated pressure, up to about 750 psi, causes an acceleration of the aging process and reduction in the required aging time from the time required for conventional heat-aging, and even a further reduction in aging time from the time required for non-hydrothermal accelerated

heat-aging at conditions of lower temperature and ambient pressure.

Hydrothermal-aging alone, with no adjustment of the initial pH of the starting calcium carbonate, causes faster rearrangement of the calcium carbonate crystal morphology than under the initial pH-adjusted, lower temperature, ambient pressure accelerated heat-aging conditions of the other embodiment of the process of this invention.

It has been further found that the heat-aging crystal morphology rearrangement process is still further accelerated in another embodiment of the process of the present invention wherein heat-aging is initiated at a temperature of from about 40 to about 100° C, and the initial pH of the starting calcium carbonate is adjusted to about 6.5, followed by addition of an alkali metal hydroxide, preferably sodium hydroxide, to the calcium carbonate at the heat-aging temperature to raise the pH to from about 9.5 to about 12.0, as in the non-hydrothermal accelerated heat-aging process of the present invention, and the calcium carbonate is then hydrothermally-aged in a hydrothermal bomb under hydrothermal conditions in which the bomb is pressurized to a pressure up to about 750 psi and the temperature in the bomb is then raised to the hydrothermal temperature at the bomb pressure, of up to about 300° C, at which conditions even more rapid rearrangement of the calcium carbonate crystal morphology occurs, resulting in an even shorter overall heat-aging time.

It has been found that the optical properties of paper, particularly brightness, are greatly improved by utilizing heat-aged calcium carbonate having a surface area of from about 3 to about 15 m²/g, an average discrete particle size of from about 0.2 to about 0.9 microns, wherein the discrete particles have an aspect ratio less than 2, and a particle size distribution such that at least about 60 weight percent of the particles lie within 50 percent of the equivalent discrete particle average spherical diameter, as a filler material during papermaking. While any heat-aged calcium carbonate having the desired physical properties is effective, that produced according to the accelerated heat-aging process and the hydrothermal-aging process of the present invention, is highly desirable in that it is fast and economical to produce on a large scale in the quantities required for papermaking.

The nature and scope of the present invention may be more fully understood in view of the following non-limiting examples.

All calcium carbonate referred to in the following examples was precipitated from lime produced at the Pfizer quarry in Adams, MA. All reactions were conducted on either a 4 or 30 liter scale.

EXAMPLE 1: Accelerated heat-aging

Typically, when precipitated calcium carbonate is made, the reaction is complete when the pH of the system reaches 8.0. After the endpoint, the pH of the system rises to approximately 9.5 due in part to the unreacted Ca(OH)₂ in the system. However, solubility product calculations done to determine the effect of Ca(OH)₂ on the solubilization and precipitation of calcium carbonate at elevated pH indicate that Ca(OH)₂ in solution retards the aging. Additionally, solubility product calculations also indicate that the optimum pH for aging calcium carbonate is 10.2 - 11.5 although aging occurs at other basic pH's.

Precipitated calcium carbonate having less than 0.1 micron particle size, referred to herein as "ultrafine", and a surface area of from about 25 to about 40 m²/g, was endpointed at pH of 6.7 to eliminate as much Ca(OH)₂ as possible. The product was screened to eliminate impurities, and 2400g of the product in a 10% by weight slurry was heated to 80° C. At 80° C, the pH of the slurry was again brought down to 6.7 with carbon dioxide, and 48g of sodium hydroxide was added to the slurry (2% by weight) to bring the pH up to an optimum aging pH of 10.9 - 11.1. Within one hour, the viscosity increased approximately 40-fold. Samples were taken every hour for surface area determination. The aging reaction was observed to proceed at an accelerated rate. By this process, a product surface area in the range of 8 m²/g was achieved within 4-8 hours as compared to over 22 hours by a normal aging process. Figure 1 shows the comparison between ultrafine that was aged by the accelerated process and a conventional aging process.

EXAMPLE 2: Uniqueness of particle morphology by accelerated heat-aging.

Fresh 30 liter batches of ultrafine precipitated calcium carbonate in which no additives were used during slaking, carbonation, or post-carbonation were aged by the accelerated heat-aging process described in

Example 1. The aging temperature was 80 °C and the pH was 10.5. The aged products, with surface areas ranging from 18.2 to 7.4 m²/g, were evaluated in hand sheets. The final particle morphology of ultrafine precipitated calcium carbonate particles was rhombohedral, with a final particle size of about 0.3 - 0.5 microns. The particle size distribution of this material, showing its narrow size distribution, wherein at least
 5 about 60 weight percent of the particles lie within 50 percent of the equivalent discrete particle average spherical diameter, is shown in Figure 2. Figure 3 is a photomicrograph of the crystal morphology of particles heat-aged by the accelerated heat-aging process of this invention. This figure should be compared to Figure 4 which is a photomicrograph of the crystal morphology of non-heat-aged precipitated calcium carbonate having a scalenohedral rosette structure, which was heretofore the best known filler for achieving
 10 enhanced optical properties in paper.

The results of the hand sheet study indicated that the heat-aged products had superior optical properties than the industry's best non-heat-aged scalenohedral precipitated calcium carbonate. This is shown in Figures 5, 6, and 7. The study also indicated that for a heat-aged precipitated ultrafine calcium carbonate made from Adams, MA lime, the best surface area for optical performance is 10 - 5 m²/g as
 15 shown in Figures 8 and 9.

EXAMPLE 3: Comparison of particle morphologies for different precursors.

Numerous materials such as ultrafine and scalenohedral precipitated calcium carbonates were heat-
 20 aged to surface areas between 8 and 12 m²/g with particle sizes of from about 0.40 to about 0.55 microns by the accelerated heat-aging process of Example 1. Table 1 lists the properties of the starting materials and the aged materials.

TABLE 1

<u>Sample Number</u>	<u>Initial Morph.</u>	<u>Initial S.A.(1)</u>	<u>Final Morph.</u>	<u>Aged SSA(1)</u>	<u>PSD(2)</u>
30 Sample 1	Ultrafine	42.2	Rhombohedral	8.6	.473
Sample 2	Scalenohedral	19.4	Prismatic	9.6	.455

35 Properties of samples submitted for handsheet evaluation to compare the optical properties of aged calcium carbonates with rhombohedral morphology vs. prismatic morphology.

- (1) SSA: Specific Surface Area in m²/g.
 (2) PSD: 50% Particle Size Distribution in microns.

40 Aging a precursor such as ultrafine resulted in a final product having a rhombohedral morphology. Aging a scalenohedral precursor resulted in a final product having a prismatic morphology. This can be clearly seen in Figures 10, 11, 12 and 13, which show the comparison between the precursors and the aged products. All the materials listed in Table 1 were evaluated in laboratory hand sheets. The results of the
 45 study indicated that even though the surface areas and particle sizes of the products were similar regardless of the precursor, the product morphology has a significant effect upon the optical properties of the particle. Rhombohedral particles exhibited superior optical properties over prismatic particles. The optical performance of the prismatic particles was comparable to or lower than that of the current industry standard scalenohedral calcium carbonate. However, in all cases, aging improved brightness. The results of
 50 the handsheet study are shown in Figures 14, 15, and 16.

EXAMPLE 4: Optimum accelerated heat-aging temperature.

Three different heat-aging temperatures 40, 60, and 80 °C were compared to determine the effect of
 55 temperature on the heat-aging rate of calcium carbonate. The pH of the aging reaction was 10.5. As was expected, the rate of aging, as determined by the surface area of the aged material, was positively correlated with the aging temperature; that is, the rate of aging was faster at a higher aging temperature. The sample that was aged at 60 °C aged similarly to the sample aged at 80 °C, with respect to the final

surface area of the product, except that the reaction lagged approximately 10-15 hours behind the 80 °C reaction. The surface area of the products from the 40 °C aging did not change significantly even after 45 hours of aging. The surface area of heat-aged ultrafine versus the heat-aging time for each of the three temperatures is shown in Figure 17.

5

EXAMPLE 5: Hydrothermal processing.

Since the aging reaction proceeds faster at high temperature, it was assumed that a sample that is aged hydrothermally attains a low surface area at a much faster rate than a sample that is aged at 80 °C at ambient pressure.

A batch of ultrafine precipitated calcium carbonate (surface area 38 m²/g) was synthesized without additives and endpointed at pH 8.0. A sample of this material was slurried to a 10% by weight solids content and 1800 ml of the slurry was placed into a 4 liter PARR hydrothermal bomb. The temperature was raised to 200 °C at 500 psi, within one hour, held at 200 °C for one hour and cooled for a total aging time of 2.5 hours. The surface area of the product was 15.7 m²/g, which would have taken 7 hours to attain under conventional heat-aging conditions.

EXAMPLE 6: Hydrothermal-aging via accelerated aging process.

A batch of ultrafine precipitated calcium carbonate (surface area 38 m²/g) was divided into two portions, A and B. Portion A was aged by the method described in Example 1. Portion B was treated in a similar manner as portion A, as described in Example 1, up to and including the point where the sample was heated to 80 °C and NaOH was added. At this point, portion B was placed into a 4 liter PARR hydrothermal bomb where the temperature was raised to 200 °C at 500 psi. Portion B was kept at these conditions for 1 - 1.5 hours at which point the material was quenched to room temperature to prevent further aging. Figure 18 shows the comparison of the aging rates between 80 °C and 200 °C where it can be seen that a decrease in surface area occurs at a much faster rate when the starting material is hydrothermally-aged.

The morphology of the hydrothermally-aged product is shown in Figure 19.

30 Claims

1. Calcium carbonate characterized by a blocky six-sided rhombohedral crystal morphology, with a surface area of from about 3 to about 15 m²/g, an average discrete particle size of from about 0.2 to about 0.9 microns, wherein the discrete particles have an aspect ratio less than 2, and a particle size distribution such that at least about 60 weight percent of the particles lie within 50 percent of the equivalent discrete particle average spherical diameter.
2. A process for rearranging the crystal morphology of calcium carbonate to a final form having a surface area of from about 3 to about 15 m²/g and an average particle size of from about 0.2 to about 0.9 microns, from an initial morphology having a surface area of greater than about 15 m²/g and a discrete average particle size of from about 0.01 to about 0.8 microns, the process being characterized by the steps of:
 - a) initiating heat-aging of the calcium carbonate by heating it to an aging temperature of from about 40 to about 100 °C at ambient pressure;
 - b) adjusting the pH of the calcium carbonate at the aging temperature to about 6.5;
 - c) adding an alkali metal hydroxide to the calcium carbonate at the aging temperature to raise the pH to from about 9.5 to about 12.0;
 - d) maintaining the calcium carbonate at the aging temperature for a sufficient time to cause the morphology of the calcium carbonate to rearrange to the final form; and
 - e) terminating heat-aging to fix the morphology of the calcium carbonate in the final form.
3. The process according to claim 2 wherein the calcium carbonate is in a form selected from the group consisting of a dry powder and an aqueous slurry.
4. The process according to claim 3 wherein the aqueous slurry contains about 10 weight percent calcium carbonate solids.
5. The process according to claim 2 wherein the alkali metal hydroxide is sodium hydroxide.

6. The process according to claim 2 wherein the aging time ranges from several minutes for calcium carbonate having an initial average discrete particle size of from about 0.01 to about 0.5 microns and a high purity to several hundred hours for calcium carbonate having at least one of an initial average agglomerate particle size of from about 0.5 to about 2 microns and containing about 5 weight percent impurities.
7. The process according to claim 2 wherein heat-aging is terminated by at least one of temperature reduction to below 40 °C and pH reduction of the calcium carbonate.
8. The process according to claim 7 wherein temperature reduction is by quenching.
9. The process according to claim 7 wherein pH reduction is by addition of CO₂ or of a polybasic acid.
10. The process according to claim 9 wherein the polybasic acid is phosphoric acid.
11. The process according to claim 2, further characterized by including a step, performed between steps (c) and (d), of further accelerating heat-aging by placing the calcium carbonate, which has been treated up to and including step (c) of the process, in a hydrothermal bomb, which is pressurized to a pressure up to about 750 psi and in which the temperature is raised to a hydrothermal-aging temperature, at the bomb pressure, of up to about 300 °C, and wherein the aging temperature in step (d) is the hydrothermal-aging temperature.
12. A process for rearranging the crystal morphology of calcium carbonate to a final form having a surface area of from about 3 to about 15 m²/g and an average particle size of from about 0.2 to about 0.9 microns, from an initial morphology having a surface area of greater than about 15 m²/g and a discrete average particle size of from about 0.01 to about 0.8 microns, the process being characterized by the steps of:
 - a) placing calcium carbonate in a hydrothermal bomb;
 - b) pressurizing the bomb to a pressure up to about 750 psi;
 - c) raising the temperature in the bomb to a hydrothermal-aging temperature at the bomb pressure of up to about 300 °C;
 - d) maintaining the calcium carbonate at the hydrothermal-aging temperature for a sufficient time to cause the morphology of the calcium carbonate to rearrange to the final form; and
 - e) terminating hydrothermal-aging to fix the morphology of the calcium carbonate in the final form.
13. Calcium carbonate produced according to the process of claim 2 wherein the final crystal morphology is rhombohedral when the initial crystal morphology is small spherical discrete particles.
14. Calcium carbonate produced according to the process of claim 2 wherein the final crystal morphology is prismatic when the initial crystal morphology is scalenohedral.
15. A method for improving the optical properties of paper characterized by utilizing calcium carbonate having a blocky six-sided rhombohedral final crystal morphology, with a surface area of from about 3 to about 15 m²/g, an average discrete particle size of from about 0.2 to about 0.9 microns, wherein the discrete particles have an aspect ratio less than 2, and a particle size distribution such that at least about 60 weight percent of the particles lie within 50 percent of the equivalent discrete particle average spherical diameter, as a filler in papermaking.

FIG. 1.




FIG. 2.




FIG. 3.




FIG. 4.




FIG. 5.




FIG. 6.




FIG. 7.




FIG. 8.




FIG. 9.




FIG. 10.




FIG. 11.




FIG. 12.



FIG. 13.




FIG. 14.




FIG. 15.




FIG. 16.




FIG. 17.




FIG. 18.





FIG. 19.





European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 91 30 1797

DOCUMENTS CONSIDERED TO BE RELEVANT					
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)		
X,Y	GB-A-5 400 44 (PITTSBURGH PLATE GLASS) * page 1, line 86 - page 2, line 1; claims 1-13 * - - - -	1-9,7-10	C 01 F 11/18 D 21 H 17/67		
Y	EP-A-0 179 597 (PFIZER) * page 8, lines 3 - 13; claim 9 * - - - -	7-10			
X,A	EP-A-0 010 643 (VEREINIGTE ALUMINIUM WERKE) * the whole document * - - - -	12,11			
A	US-A-3 320 026 (WALDECK) * column 3, line 38 - column 4, line 12; figures 4-6 * - - - - -	1,13-15			
			TECHNICAL FIELDS SEARCHED (Int. Cl.5)		
			C 01 F		
The present search report has been drawn up for all claims					
Place of search The Hague		Date of completion of search 17 June 91	Examiner ZALM W.E.		
<table border="0"><tr><td>CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention</td><td>E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons ----- &: member of the same patent family, corresponding document</td></tr></table>				CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention	E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons ----- &: member of the same patent family, corresponding document
CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention	E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons ----- &: member of the same patent family, corresponding document				